



Test results of PS 7100-F

Description	Standard	Condition	Result	Unit
Tensile strength @Yield	ISO 527	Speed 5 mm/min Grip 115 mm	18.33	Mpa
Elongatin @ Break	ISO 527	Speed 5 mm/min Grip 115 mm	7.28	%
Tensile strength @ Break	ISO 527	Speed 5 mm/min Grip 115 mm	16.33	Mpa
Elongatin @ Yield	ISO 527	Speed 5 mm/min Grip 115 mm	3.03	%
Flexural Modulus	ASTM D790	Speed: 1.3mm/min Deflection: 0.5mm	2197	Mpa
Flexural strength	ASTM D790	Speed: 1.3mm/min Deflection: 5.0mm	37.85	Mpa
MFI	ASTM D1238	5.00 kg / 200 °C	8.2	g/10 min
Filler Content	ISO3451/1	600°C/30 min	7.21	%
DSC	ISO 11357/6	10 °C/min N2 50ml/min	Click here	°c
Density	ISO 1183	23°C, 50% RH	1.08	gr/cm ³



- The uncertainty of the test result is based on confidence range of %95 and K=2 which is calculated and Announced due to the customers' demands.



Info@exirpolymer.com



+98 31 4564 3030



+98 912 962 3265



Exirpolymer.com



Fa.Exirpolymer.com



Ar.Exirpolymer.com